

**This Page Is Inserted by IFW Operations
and is not a part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- **BLACK BORDERS**
- **TEXT CUT OFF AT TOP, BOTTOM OR SIDES**
- **FADED TEXT**
- **ILLEGIBLE TEXT**
- **SKEWED/SLANTED IMAGES**
- **COLORED PHOTOS**
- **BLACK OR VERY BLACK AND WHITE DARK PHOTOS**
- **GRAY SCALE DOCUMENTS**

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

Sub
C
B
Contd

and that repeated torsion value RT (turns/100D) of the steel wire, which is defined as sum of forward twisting and reverse twisting given until a crack is formed on a steel wire in a test wherein a steel wire is subjected to a repetition of forward twisting equivalent to 3 turns per 100D and reverse twisting to the original state with the axis of the steel wire kept straight, satisfies following formula;
 $\log RT \geq 2 - 0.001 \{TS - (2250 - 1450 \log D)\}.$

2. (Amended) A steel wire according to claim 1, having tensile strength TS (N/mm²) satisfying following formulas,
 $TS \geq 2750 - 1450 \log D.$

6. (Amended) A method of manufacturing a steel wire according to claim 8, wherein ϵ at the final die is set from 3.5 to 4.2.

b2

7. (Amended) A method of manufacturing a steel wire according to claim 8, wherein a bending operation with tension is applied to the steel wire drawn through the final die.

8. (New) A method of manufacturing a steel wire comprising; a wire diameter ranging from 0.10mm to 0.40mm obtained by subjecting a high-carbon steel wire material having a carbon content ranging from 0.70% to 0.90% in weight to heat treatment and wire drawing, characterized in;

a tensile strength TS (N/mm^2) of the steel wire satisfies following formula,

$TS \geq 2250 - 1450 \log D$

wherein D is the diameter of the steel wire in mm and log means common logarithm,

and that repeated torsion value RT (turns/100D) of the steel wire, which is defined as sum of forward twisting and reverse twisting given until a crack is formed on a steel wire in a test wherein a steel wire is subjected to a repetition of forward twisting equivalent to 3 turns per 100D and reverse twisting to the original state with the axis of the steel wire kept straight, satisfies following formula-

$\log RT \geq 2 - 0.001 \{TS - (2250 - 1450 \log D)\},$

said method comprising the steps of heat treating drawing a high-carbon steel wire material after heat treatment, wherein the step of drawing is carried out according to following conditions;

1. reduction per die is set ~~from~~^{from} $(22.67 \epsilon + 3)\%$ to 29% for dies at which ϵ is less than $\epsilon = 0.75$, 11/21/01
2. reduction per die is set from 20% to 29% for dies at which ϵ is not less than 0.75 and not more than 2.25,
3. reduction per dies is set from $(-5.56 \epsilon + 32.5)\%$ to $(-6.22 \epsilon + 43)\%$ for dies at which ϵ is more than 2.25 except for the final die,

AMENDMENT UNDER 37 C.F.R. § 1.111
U.S. Application No.: 09/424,300

4. reduction per die is set from 4% to $(8.3 \epsilon + 40.6)\%$ for the final die, and

5. ϵ at the final die is set from 3.0 to 4.3,

wherein ϵ is drawing strain expressed by a formula $\epsilon = 2\ln(d_0/d)$, d_0 is diameter of the steel wire material in mm before drawing, d is diameter of the steel wire in mm after passing through a die, and \ln means natural logarithm.

B3
Control

9. (New) A steel wire comprising wire diameter ranging from 0.10mm to 0.40mm obtained by subjecting a high-carbon steel wire material having a carbon content ranging from 0.70% to 0.90% in weight to heat treatment and wire drawing,

the steel wire manufactured by drawing a high-carbon steel wire material after heat treatment, wherein the drawing is carried out according to following condition;

1. reduction per die is set form $(22.67 \epsilon + 3)\%$ to 29% for dies at which ϵ is less than 0.75,

2. reduction per die is set from 20% to 29% for dies at which ϵ is not less than 0.75 and not more than 2.25,

3. reduction per dies is set from $(-5.56 \epsilon + 32.5)\%$ to $(-6.22 \epsilon + 43)\%$ for dies at which ϵ is more than 2.25 except for the final die,

4. reduction per die is set from 4% to $(8.3 \epsilon + 40.6)\%$ for the final die, and

5. ϵ at the final die is set from 3.0 to 4.3,

wherein ϵ is drawing strain expressed by a formula $\epsilon = 2\ln(d_0/d)$, d_0 is diameter of the steel wire material in mm before drawing, d is diameter of the steel wire in mm after passing through a die,

AMENDMENT UNDER 37 C.F.R. § 1.111
U.S. Application No.: 09/424,300

and \ln means natural logarithm and the tensile strength TS (N/mm^2) of the steel wire satisfies following formula,

$$TS \geq 2250 - 1450 \log D$$

wherein D is the diameter of the steel wire in mm and \log means common logarithm,

and that repeated torsion value RT (turns/100D) of the steel wire, which is defined as sum of forward twisting and reverse twisting given until a crack is formed on a steel wire in a test wherein a steel wire is subjected to a repetition of forward twisting equivalent to 3 turns per 100D and reverse twisting to the original state with the axis of the steel wire kept straight, satisfies following formula,

$$\log RT \geq 2 - 0.001 \{TS - (2250 - 1450 \log D)\}$$

10. (New) A steel wire according to claim 9, having tensile strength TS (N/mm^2) satisfying following formula.

$$TS \geq 2750 - 1450 \log D.$$

11. (New) A steel wire according to claim 10, having repeated torsion value RT not less than 60% of RT of the same steel wire the surface layer of which has been removed by the amount equivalent to 10% of total volume.

AMENDMENT UNDER 37 C.F.R. § 1.111
U.S. Application No.: 09/424,300

B3
Cont'd

12. (New) A steel wire according to claim 9, having breaking torsion value, which is defined as an amount of twisting to one direction subjected to a steel wire until the steel wire is broken, not less than 20 turns per 100D when the steel wire has been given such a preforming that the steel wire has minimum radius of curvature of 10 to 60 times its diameter and embedded in rubber and taken out from the rubber after vulcanization.
